

RECOATING

#7601/#7604/#7611/#7614 may be recoated after a 16 Hour dry at 77° F, or upon cool down after force drying at 140° F for 40 minutes. After 8 hours dry time primer must be sanded before topcoating.

POT LIFE

Pot life will be 1 1/2 - 2 hours at 77° F.

FISH EYE

Do not use fisheye eliminator in this product.

PAINTING FLEXIBLE PARTS

A flexible additive may be needed when painting certain flexible parts. Follow manufacturers recommendations.

EQUIPMENT CLEAN-UP

Clean equipment immediately after use with gun wash or a high quality lacquer thinner.

TECHNICAL DATA

Mixing Ratio:	4:1
Viscosity (RTS):	18-20 seconds #2 Zahn
Weight Solids (RTS):	54.51 - 54.65%
Volume Solids (RTS):	34.08 - 34.19%
Film Build:	1.0 - 1.5 mils per full wet coat
Coverage:	547 - 548 sq. ft. per gallon @ 1 dry mil
V.O.C. (RTS):	4.8 lbs/gal
Disposal/Safety:	see MSDS for this product
Humidity Resistance:	Excellent
Salt Spray Resistance	Excellent

NOTE: Finish Pro products are not recommended for use in temperatures below 60° F. Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read MSDS Before Use

The contents of the package must be blended with other components before the product can be used. Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE MSDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.