

ACL1700-44:1 Just CLEAR

PRODUCT# DESCRIPTION

ACL1700-4 JUST CLEAR URETHANE CLEARCOAT

ACTIVATOR

BCL1702-6 JUST CLEAR FAST ACTIVATOR
BCL1703-6 JUST CLEAR MEDIUM ACTIVATOR
BCL1704-6 JUST CLEAR SLOW ACTIVATOR

DESCRIPTION

ACL1700-4 Just Clear Urethane Clearcoat has excellent performance and appearance at an economical price. ACL1700-4 Just Clear Urethane Clearcoat flows out to a smooth, durable finish with excellent gloss.

MIXING

Mix 4 Parts ACL1700-4 Just Clear Urethane Clearcoat to 1 Part BCL1702-6, BCL1703-6 or BCL1704-6 Just Clear Activator.

APPLICATION

Apply 2-3 medium wet coats at 35-40 psi or (8-10 psi at the gun when using HVLP), allowing a 10 minute flash between coats at 77°F.

DRYING AT 77°

DUST FREE 15 MINUTES
TACK FREE 30 MINUTES
TO DELIVER 18 - 24 HOURS
TO BUFF 18 - 24 HOURS

FORCE DRYING

FLASH TIME @ 77° F 15 MINUTES BAKE TIME @ 140° F 30 MINUTES

Allow a 1 to 2 hour cool-down time before wet sanding or buffing after force drying.

TECHNICAL DATA

Viscosity: 17 - 19 Seconds Weight Solids: 32.21% Volume Solids: 25.59% Film Build: 0.8 - 1.0 mils Coverage: 479 sg. ft.

Pot Life: 2 HOURS @ 72° F / 22° C

Manufacturer's Exclusive Limited Warranty

For Industrial use only by professional, trained personal using proper safety protective equipment. Not for sale to, or use by, the general public. Manufacturer warrants that its products are free from defect in material and workmanship at the time of sale. In the event that any product is proved by objective testing and analysis to have been defective at the time of sale, upon the return of the defective product, the manufacturer shall replace the product at no cost, excluding the shipping costs, as the exclusive remedy. This warranty does not cover damage caused by accident, misuse, improper application, improper combination of products or tampering. ALL IMPLIED WARRAN-TIES WHETHER IT BE OF MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. THIS WARRANTY EXCLUDES ALL INCIDENTAL AND CONSEQUENTIAL DAMAGES.

NOTE: Products are not recommended for use in temperatures below 60° F.

Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read SDS Before Use

Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions. The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.