

PRODUCT FEATURES & APPLICATION

Dominion Sure Seal Ltd.

6175 Danville Road, Mississauga, Ontario, Canada L5T 2H7

TEL (905) 670-5411

FAX (905) 670-5174

Shake & Shoot Multi Purpose Truck Bed Liner

Stock BSSBL

Color: Black

Description: Dominion Sure Seal's new easy to use Spray In Bed Liner and Multi Purpose Coating – "SHAKE & SHOOT". This multi purpose coating can be sprayed using a Dominion Sure Seal's schutz gun (BUPA) or if preferred you can brush or roll the coating onto virtually any surface to provide a tough, durable urethane protective coating. This spectacular product is a fast drying protective coating that provides excellent UV protection. Protect your investment with "SHAKE & SHOOT" the easy to use coating that provides a nice looking, long lasting protective coating that protects your truck against a wide range of extreme condition and extends longevity of almost any surface. "SHAKE & SHOOT"

Features:

- Can be easily applied by a schutz style spray gun, brush, or roller.
- Excellent adhesion to properly prepared automotive paint, bare metal, wood, fiberglass, concrete and most plastic.
- Remains permanently flexible.
- Contains corrosion inhibitors
- Seals surfaces against moisture and corrosion.
- Greatly increases resale value of vehicles
- Easy mixing: 1. Pour Part B (Catalysts) into Part A (Resin) can. Screw cap back on. 2. Shake for 2 minutes vigorously. 3. Attach Schutz Gun and Shoot onto your surface you want to protect.
- Superior Semi-Gloss finish.
- Can vary film build for different applications
- Can vary texture to achieve different finishes.

Surface Preparation:

1. Surface to be coated must be cleaned with a good quality wax & grease remover
2. Loose paint / rust should be removed and affected areas primed
3. Sand area with 120 grit sandpaper or a TNBC Nylon Cup Brush. The surface should be sanded thoroughly to ensure adhesion. Blow off and re-clean. Surface should be clean and dust free.
4. Mask all areas surrounding application area. Additional masking may be required depending on experience.

Typical Properties Of Shake & Shoot

Pot Life of a mixed quart 60 to 70 min @ 72 F (21 C).

Warmer temperature will shorten Pot Life

Tack Free/Dry to touch: 1 to 1.5 hours @ 72 F (21 C)

Depending on film build

Light duty: 48 hours @ 72 F (21 C)

Regular duty: 5-7 days @ 72 F (21 C)

Do not expose to water for 24 hours @ 72 F.

Application:

**Mix/Shake and Shoot only one quart at a time.*

1. Pour contents of Parts B (Catalyst) into Part A (Resin) can only to fill line on the can. Screw cap back onto Part A can. Do not overfill. You must leave room in Part A can to allow the product to be shaken to be mixed.
2. Shake catalyzed Part A can vigorously for 2 minutes.
3. Remove cap and attach Dominion Sure Seal's Schutz Gun (BUPA) onto Part A can and spray onto the surface to be coated. *** Set air pressure at the schutz gun between 40 – 60 psi. Apply in an even sweeping motion. Spray one coat to get coverage. If a **light dust coat** is needed to even texture apply once first spray coat is finished. If a second coat is wanted allow the first coat to flash a minimum of 30 – 45 minutes prior to applying a second coat.

** If Brushing or Rolling **

1. After shaking catalyzed part A can pour contents onto the surface to be coated.
A) Brush – Brush in even strokes until sufficient coverage is attained. Allow the product to *flash between coats. Brush may be cleaned or rinsed with lacquer thinner.
B) Roller - using a ¼ - 3/8 inch pile solvent resistant roller, apply even coats until desired finish is achieved. Allow the product to *flash between coats.

**** Clean equipment immediately after finished spraying.**

An additional coat may be applied after allowing to flash. Flash time depends on thickness, temperature, and humidity. Average time is 30 – 45 minutes at 72 degrees F. (21 C). If a second coat is going to be applied you must apply the second coat after the 30-45 min flash but before allowing the product to sit for more than 2 hours at 72 F (21 C) (Maximum recoat window). Hotter temperatures shorten flash times and maximum recoat window. If not sure about flash time or recoat window allow to dry, scuff sand and apply second coat.

Coverage:

Shelf Life: 12 months at 21 C / 72 F

Practical Coverage: 80-84 sq. ft. per kit @ 7-8 mls dry

1 kit will cover a full size short be truck box at 7-8 mls dry. If a thicker coat is sprayed or applied in multiple coats additional material may be needed.